

PVC HIGH-GLOSS DECO SHEET 0,3 MM X 1270 MM

Thickness DIN EN ISO 2286-3	300 $\mu\text{m} \pm 10 \mu\text{m}$
Color Tolerance X-Rite Ci6x-Ci7 / d65/10° / CIELAB	ΔE^* : $\leq 0,8$ ΔL^* : $\pm 0,4$ Δa^* : $\pm 0,35$ Δb^* : $\pm 0,4$
Density	$\geq 1,5 \text{ g/cm}^3$
Tensile Strength ISO 527-3	Longitudinal: $\geq 45 \text{ N}$ Transversal: $\geq 40 \text{ N}$
Elongation at Break ISO 527-3	Longitudinal: $\geq 20 \%$ Transversal: $\geq 25 \%$
Scratch Resistance TS RN 15186 / DIN EN ISO 68861-4	$\leq 0,3 \text{ N}$
Gloss Level Rhopoint 20 ° Gloss Meter	$\geq 80 \text{ GU}$ $\geq 80 \text{ DOI}$
Light Fastness DIN EN ISO 4892-2/105 B02 TS EN 15187	$\leq 0,6$ (Xenon: 200 hr) ΔE^*
Scratch Resistance (Pencil Hardness) TS EN ISO 15184	$\uparrow \text{ HB}$
Adhesion Test (Cross Cut) ASTM D 3359-17	5 B Value "0" (No separate)
Dyne Pen Test ASTM D 2578	36 mN/m

* This technical information sheet represents our latest state of knowledge and shall inform without obligation

STORE CONDITIONS:

- * Store in a dry clean environment at room temperature with moderate humidity. The material can be suspended in unopened packaging. Store away from sources of heat and sunlight.
- * Material should be acclimatised 72 hours prior to use at room temperature (about 20 ° C)
- * When the above conditions are met, it is recommended that primer applied products should be used within 24 months.