

## AdoFilm Technical Data For Decorative Films

<b>Thickness (DIN EN ISO 2286-3)</b>	160 $\mu\text{m} \pm 10 \mu\text{m}$
<b>Color Tolerance (DIN 53236 (45/0), 1983-01)</b>	$\Delta E \leq 0,6$ $\Delta L \leq +/-0,35$ $\Delta a \leq +/- 0,30$ $\Delta b \leq +/-0,35$
<b>Density</b>	$\geq 1,3 \text{ g/cm}^3$
<b>Tensile Strength ISO 527-3</b>	Longitudinal: $\geq 15 \text{ N}$ Transversal: $\geq 25 \text{ N}$
<b>Elongation at Break ISO 527-3</b>	Longitudinal: $\geq 3 \%$ Transversal: $\geq 3 \%$
<b>Dimensional Stability DIN 53377</b>	Longitudinal: Max. $- 6 \%$ Transversal: Max. $- 2,4 \%$
<b>Light Fastness DIN EN ISO 4892-2 / 105 B 02 TS EN 15187</b>	$\geq 6$ / Blue Scale
<b>Dyne pen test ASTM D 2578</b>	$\geq 30 \text{ mN/m}$

\* This technical information sheet represents our latest state of knowledge and shall inform without obligation

**STORE CONDITIONS:**

- \* Store in a dry clean environment at room temperature with moderate humidity. The material can be suspended in unopened packaging. Store away from sources of heat and sunlight.
- \* Material should be acclimatised 72 hours prior to use at room temperature ( about 20 ° C)
- \* When the above conditions are met, it is recommended that primer applied products should be used within 24 months.